

# Technical Data Sheet

## Type II/V Portland Cement

**Product Description:** DMI Type II/V Cement meets the ASTM C150 standards for both Type II and Type V Portland Cement for low alkali and moderate sulfate resistance necessary to the western US. This is a general, all purpose cement for making high strength mortars or structural concrete for foundations, Sidewalks, structures, slabs. Footings, walls, hardscape, pools, etc.

### Physical Properties:

pH Value	12-13
Absorption Performance (by wt. with H <sub>2</sub> O)	~150%
Specific Gravity	3.1—3.2
Bulk Density	55-70 pcf
Stackability	<0.5 hrs
<b>Compressive Strengths</b>	
1 day	1720 psi
7 days	4200 psi

**Available Packaging:** Bulk, 3000 lbs. bags, 2000 lbs. bags, 94 lbs. bags, and 50 lbs. bags can also provide on-site storage

The data in the Technical Data Sheet related only to the specific material designated herein and does not relate to use in combination with any other material on or in any process. Diversified Minerals Inc. (DMI) believes the information contained herein is accurate; however, DMI makes no guarantees with respect to such accuracy and assumes no liability in connection with the use of the information contained herein which is not intended to be and should not be construed as legal advice or as insuring compliance with any federal, state or local laws or regulations. Any party using this product should review all such laws, rules, or regulations prior to use, including but not limited to Federal, Provincial, State and Local regulations.

**NO WARRANTY IS MADE, EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR OTHERWISE.**